SUNSHINE like brick paint

厦光仿砖涂料



产品简介: 厦光仿砖涂料由高分子合成树脂和构成纹理的骨料等材料组成,该产品具有优异的防水性和柔韧性,自重 轻、附着力强、纹理多样、色彩丰富,与外墙外保温完美地匹配,绝无安全隐患,装饰效果完全可媲美外 墙砖,是传统外墙砖替代更新产品。

Product features:


Texture paint, weather resistant pigments and polymer resins constitute texture textured materials such as fine natural quartz aggregates composed of masked crack has excellent ability, strong adhesion, water repellent breathable decoration natural, full, vivid and creative architectural beauty of nature.

■弥盖墙体裂纹 ■耐水性好,不易褪色

- 性能特点:
- 自重轻,无安全风险
- 优异防水性,避免渗水漏水
- 耐碱性好,解决外墙砖泛碱缺点 与外墙外保温匹配性好
- 附着力强,不脱落 ■色彩丰富、媲美外墙砖

· Strong adhesion and not fall off

- Application of places
- Masked wall cracks
- · Good water resistance, resists fading · Resistant to avoid water leaking Good alkali resistance
- · Light weight, no security risk · Outer thermal insulation and good matching
 - · Comparable to the rich colors



适用场所:

适用于高档商住楼、多层公寓、住宅小区,非常适合于外墙外保温墙面, 为用户提供绝佳安全保证。

Application of places

Apply on the high quality commercial and residential buildings, high-rise apartment, residential, is ideally suited for exterior wall thermal insulation wall, provides users with excellent security.

技术参数:

料: 纯丙烯酸共聚乳液。 色 : 厦光仿砖涂料样板册所示颜色或提供来样。

产品特征:水溶性、彩色、厚质。 干燥时间:表干12小时,重涂时间24小时,实干48小时。(温度25℃,

相对湿度80%) 理论耗漆量 : 质感仿砖1.50~2.50kg/m²、天然石仿砖2.00~3.50kg/m²,

陶彩砖2.00~3.50kg/m², 实际视基面粗糙程度, 施工方法 不同有所差异。 **Technical parameters**

Base material: acrylic polymer emulsion.
Product features: water soluble, thick paste type, flexible/flexible series.
Drying time: dry for 12 hours, Recoat time 24 hours, work for 48 hours. (Temperature 25°C, relative humidity 80%)
consumption of paint: 1.50~2.50kg/m² textured faux brick, natural stone imitation-brick 2.00~3.50kg/m², Tao Cai brick 2.00~3.50kg/m², but the actual surface roughness, construction methods varied.

Construction of wind, rain and other inclement weather should

陶彩砖涂料

施 工:

施工方法: 批刮、喷涂。 稀释比例:一般不宜加水稀释,确因施工困难,可酌加5%以内清水稀释。 施工要求:在5℃~35℃及相对湿度80%以下施工。大风、下雨等恶劣天气

应避免施工。

Technical parameters

Construction method: rubbing, spraying, Dilution ratio: generally should not be diluted with water, because of engineering problems, may be subject to additional 5% less than clear water dilution

Construction requirements: 5° C \sim 35 $^{\circ}$ C and relative humidity below 80% construction.

be avoided. 性能比较:

Technical parameters:

项 目

heavy 防水性	25-40kg/m ² 一般	2.0~4.5kg/m² 好
Waterproof 耐碱性 Durability	Seneral 返碱,影响美观 Long	Good 不返碱,保持长久美观
柔韧性 Flexibility	网 性 Rigidity	Long 柔性 Flexible
安全性 Security	会发生脱落,有伤人/损物可能 Shedding, and the possibility of wounding damage things	无安全隐患 No security risks
与保温匹配性 Matching and thermal insulation	差,易开裂 Poor, easy to crack	好,不易开裂 Well, not easy to crack

外墙砖

